

# IL CAMPO®

**UNILOCK®**

TECH SHEET

THICKNESS 70MM

REGION OHIO




EDGE  
MICRO BEVEL DETAIL



**UNILOCK®** Exclusive Technologies

ENDURACOLOR



## APPLICATIONS


Note: Not all sizes are suitable for every application. Contact Unilock Representative for assistance.



Driveway




Patio & Walkway



Borders and Accents

## COLORS


GRANITE FUSION  
FINISH: IL CAMPO -  
BRUSHED



**UNIT A**  
125mm x 169mm x 70mm  
4 7/8" x 6 3/4" x 2 3/4"




**UNIT B**  
125mm x 262.5mm x 70mm  
4 7/8" x 10 3/8" x 2 3/4"




**UNIT C**  
125mm x 337.5mm x 70mm  
4 7/8" x 13 3/8" x 2 3/4"



**UNIT D**  
125mm x 450mm x 70mm  
4 7/8" x 17 3/4" x 2 3/4"



**UNIT E**  
187.5mm x 225mm x 70mm  
7 1/2" x 8 7/8" x 2 3/4"



**UNIT F**  
187.5mm x 337.5mm x 70mm  
7 1/2" x 13 3/8" x 2 3/4"



**UNIT G**  
187.5mm x 450mm x 70mm  
7 1/2" x 17 3/4" x 2 3/4"


**MOCHA BROWN  
FINISH: IL CAMPO -  
BRUSHED**




**4"X8"**  
100mm x 200mm x 70mm  
3 7/8" x 7 7/8" x 2 3/4"

JOINT SPACING = 3MM


## LAYING PATTERNS




LP PROMENADE MULTI UNIT  
RANDOM G




LP PROMENADE 4X12 RB H




LP PROMENADE 4X12 HB I



LP PROMENADE 8X24 RB A




LP PROMENADE 8X24 HB C



LP ARTLINE FIXED RANDOM A

**TYPICAL CROSS SECTION**

Note: Base, screed bed, infill aggregates and or reinforcements may vary based on project requirements or as specified by engineer.



**PACKAGING**

	(70) RANDOM RANDOM BUNDLE	4"X8"	4"X8"	4"X12"	8"X24"
<b>UNIT THICKNESS (MM)</b>	70	70	60	100	100
<b>LAYERS PER BUNDLE</b>	8	8	9	5	5
<b>SQ FT PER BUNDLE</b>	93.25	94.40	106.20	58.13	51.67
<b>SQ FT PER LAYER</b>	11.66	11.80	11.80	11.63	10.33
<b>SQ FT PER UNIT</b>	0.49	0.22	0.22	0.32	1.29
<b>UNITS PER BUNDLE</b>	192	432	486	180	40
<b>UNITS PER LAYER</b>	24	54	54	36	8
<b>LIN FT PER BUNDLE - SOLDIER</b>	141.73	159.45	59.06	26.25	-
<b>LIN FT PER LAYER - SOLDIER</b>	17.72	17.72	11.81	5.25	-
<b>LIN FT PER UNIT - SOLDIER</b>	0.33	0.33	0.33	0.66	-
<b>LIN FT PER BUNDLE - SAILOR</b>	283.46	318.90	177.17	78.74	-
<b>LIN FT PER LAYER - SAILOR</b>	35.43	35.43	35.43	15.75	-
<b>LBS PER BUNDLE</b>	2,911.27	2,898.46	2,763	2,658.87	2,391
<b>LBS PER LAYER</b>	363.91	362.31	307	531.77	478.20
<b>LBS PER UNIT</b>	15.16	6.71	5.69	14.77	59.78

## INSTALLATION NOTES

---

### IL CAMPO®

Brushed clay brick is the best way to describe this Unilock exclusive paver. Made with EnduraColor™, Il Campo's uniquely engrained slip resistant surface features angular brush lines on the surface, creating wonderful highlights in early morning or evening lighting conditions.

Recommended Base Stabilization – one layer of DriveGrid™ stabilization grid between subgrade and base material. Recommended depth 8" to 10" below pavers for maximum stability and performance. Use under Standard Base or Permeable Base.

Standard Base – Min. 6" – 8" of ¾" Crusher Run gravel (any road base standard in accordance with ASTM-D2940) compacted to 98% Standard Proctor Density (SPD).

Standard Bedding Course – 1" thick of coarse sand– in accordance with ASTM-D2940 screeded over base.

Alternative Permeable Base – Min. 6" – 8" of ¾" clear open-graded stone compacted to achieve full particle lock-up and consolidation. (Clear open-graded does not compact but does consolidate slightly by rattling the particles together.)

Alternative Permeable Bedding Course – 1" thick of 1/4" clear open-graded chip stone – (ASTM No. 8) screeded over base.

Special Note: Concrete Direct Overlay – In some areas of the country and in some applications pavers are very successfully placed directly over concrete. Concrete as a base is in itself quite strong, but it can affect the structural integrity of the paver particularly in vehicular applications, where the concrete below is sub-par. The following considerations must be taken into account to insure that the concrete below the surface is ideal:

1. Concrete integrity – concrete must be in good condition, and not crumbling
2. Drainage slope – concrete below must be sloped away from all buildings and structures
3. Drainage holes – In lowest areas of the concrete, drill 1" holes in concrete (on 12" centers) and fill holes with ¼" chip (ASTM No. 8)
4. Base drainage - the area below the concrete must not be subject to frost movement
5. Surface - surface must be totally smooth and flat equivalent to the desired finished surface
6. Waterproofing - may be required when installing pavers over concrete where there is a basement or cold cellar below. Install an impervious rubber membrane over the surface prior to installing any pavers over the surface.
7. Jointing Sand - Use an impervious polymeric sand when installing over concrete

### Jointing Material and Joint Stabilization

All sands must meet ASTM C144 or C33 Specifications.

Good Option: Ordinary sharp jointing sand in accordance with ASTM C144 or C33. (Common name: Concrete Sand)

Best Option: Ordinary concrete sand stabilized by a water-based or solvent-based joint sand stabilizer sealer. Il Campo has a deep texture which may trap sand particles. ALWAYS blow surface off COMPLETELY before stabilizing the sand. Refer to manufacturer's application specifications and requirements.

Handling – This product has no special handling requirements.

Edge Restraint - Always install an edge restraint around the perimeter of any paver installation not restrained by building structures. Spike-in edge restraints come in plastic and metal and work well for most applications. A concrete curb or a sub-surface concrete wedge can also be installed to retain the edge.

Paver Compaction - Always use a protective polymer pad on the bottom of your compactor when doing the final compaction of the pavers. An alternative is to use a rubber-roller compactor for the final compaction.

Cleaners – Any cleaner specifically designed for pavers may be used for color restoration or general cleaning. Follow manufacturer's dilution rates and application procedures. Always test a small area to make sure the results are as expected.

### Sealers

- Product may be sealed for aesthetic or cleanliness reasons but it is not required

- Use any sealer approved for concrete pavers
- Select type for desired aesthetics
- Product must be cleaned before sealing
- Always read and follow manufacturer's application procedures
- Always test a small area to make sure the results are as expected

The Americans with Disabilities Act Accessibility Guidelines (ADAAG) provides measurable criteria to determine compliance, not individual product evaluation. Gaps, joints or openings, greater than ½" horizontal and ¼" vertical should be avoided as they can disrupt wheelchair maneuvering (United States Access Board – Guidelines and Standards).

---

Contact Unilock Representative for actual color samples and availability. Unilock reserves the right to change product information without notice.

PDF Generated December 22, 2024, 12:01 pm

