

# SERIES™

**UNILOCK®**

TECH SHEET

THICKNESS 70MM

REGION NEW YORK



EDGE  
CHAMFERED EDGE DETAIL




**UNILOCK®** Exclusive Technologies

ENDURACOLOR

## APPLICATIONS

Note: Not all sizes are suitable for every application. Contact Unilock Representative for assistance.

---



**Borders and Accents**



**Driveway**




**Patio & Walkway**

## COLORS

---


**BLACK GRANITE**  
**FINISH: SERIES -**  
**EXPOSED GRANITE**




**4"X8"**  
100mm x 200mm x 70mm  
3 7/8" x 7 7/8" x 2 3/4"

**JOINT SPACING = 3MM**

## LAYING PATTERNS




**LP SERIES 4X8 HB G**



**LP SERIES 4X8 RB F**

**TYPICAL CROSS SECTION**

Note: Base, screed bed, infill aggregates and or reinforcements may vary based on project requirements or as specified by engineer.



**PACKAGING**

	4"X8"
UNIT THICKNESS (MM)	70
LAYERS PER BUNDLE	8
SQ FT PER BUNDLE	94.40
SQ FT PER LAYER	11.80
SQ FT PER UNIT	0.22
UNITS PER BUNDLE	432
UNITS PER LAYER	54
LIN FT PER BUNDLE - SOLDIER	141.76
LIN FT PER LAYER - SOLDIER	17.72
LIN FT PER UNIT - SOLDIER	0.33
LIN FT PER BUNDLE - SAILOR	283.44
LIN FT PER LAYER - SAILOR	35.43
LBS PER BUNDLE	3,019.20
LBS PER LAYER	377.40
LBS PER UNIT	6.99

## INSTALLATION NOTES

---

### Series™

The sparkling granite, quartz and feldspar crystals embedded into the surface of Series set it apart from any other paver. With our proprietary EnduraColor™ technology, these non-fading minerals will provide endless performance with a lifetime of beauty and surface resilience.

**Recommended Base Stabilization** – one layer of DriveGrid™ stabilization grid between subgrade and base material. Recommended depth 8" to 10" below pavers for maximum stability and performance. Use under Standard Base or Permeable Base.

**Standard Base** – Min. 6" – 8" of ¾" Crusher Run gravel (any road base standard in accordance with ASTM-D2940) compacted to 98% Standard Proctor Density (SPD).

**Standard Bedding Course** – 1" thick of course sand– in accordance with ASTM-D2940) screeded over base.

**Alternative Permeable Base** – Min. 6" – 8" of ¾" clear open-graded stone compacted to achieve full particle lock-up and consolidation. (Clear open-graded does not compact but does consolidate slightly by rattling the particles together.)

**Alternative Permeable Bedding Course** – 1" thick of 1/8" clear open-graded chip stone – (ASTM No. 8 or 9) screeded over base.

**Special Note: Concrete Direct Overlay** – In some areas of the country and in some applications pavers are very successfully placed directly over concrete. Concrete as a base is in itself quite strong, but it can affect the structural integrity of the paver particularly in vehicular applications, where the concrete below is sub-par. The following considerations must be taken into account to insure that the concrete below the surface is ideal:

1. Concrete integrity – concrete must be in good condition, and not crumbling
2. Drainage slope – concrete below must be sloped away from all buildings and structures
3. Drainage holes – In lowest areas of the concrete, drill 1" holes in concrete (on 12" centers) and fill holes with ¼" chip (ASTM No. 8)
4. Base drainage - the area below the concrete must not be subject to frost movement
5. Surface - surface must be totally smooth and flat equivalent to the desired finished surface
6. Waterproofing - may be required when installing pavers over concrete where there is a basement or cold cellar below. Install an impervious rubber membrane over the surface prior to installing any pavers over the surface.
7. Jointing Sand - Use an impervious polymeric sand when installing over concrete

### Jointing Material and Joint Stabilization

All sands must meet ASTM C144 or C33 Specifications.

**Good Option:** Ordinary sharp jointing sand in accordance with ASTM C144 or C33. (Common name: Concrete Sand)

**Best Option:** Ordinary concrete sand stabilized by a water-based or solvent-based joint sand stabilizer sealer. Series has a deep texture which may trap sand particles. ALWAYS blow surface off COMPLETELY before stabilizing the sand. Refer to manufacturer's application specifications and requirements.

**Handling** – This product has no special handling requirements.

**Edge Restraint** - Always install an edge restraint around the perimeter of any paver installation not restrained by building structures. Spike- in edge restraints come in plastic and various metals and work well for most applications. A concrete curb or a sub-surface concrete wedge can also be installed to retain the edge.

**Paver Compaction** - Always use a protective polymer pad on the bottom of your compactor when doing the final compaction of the pavers. An alternative is to use a rubber roller compactor for the final compaction.

**Cleaners** – Any cleaner specifically designed for pavers may be used for color restoration or general cleaning. Follow manufacturer's dilution rates and application procedures. Always test a small area to make sure the results are as expected.

### Sealers

- Product may be sealed for aesthetic or cleanliness reasons but it is not required
- Use any sealer approved for concrete pavers

- Select type for desired aesthetics
- Product must be cleaned before sealing
- Always read and follow manufacturer's application procedures
- Always test a small area to make sure the results are as expected

The Americans with Disabilities Act Accessibility Guidelines (ADAAG) provides measurable criteria to determine compliance, not individual product evaluation. Gaps, joints or openings, greater than ½" horizontal and ¼" vertical should be avoided as they can disrupt wheelchair maneuvering (United States Access Board – Guidelines and Standards).

---

Contact Unilock Representative for actual color samples and availability. Unilock reserves the right to change product information without notice.

PDF Generated December 22, 2024, 12:26 pm

